

Preliminary Amendment
Attorney Docket No. Q68683

12. The shielded flat cable of claim 1, wherein the adhesive comprises at least one reactive compound selected from the group consisting of an acryloxy group-containing compound and methacryloxy group-containing compound in an amount of 0.5 to 80 parts by weight based on 100 parts by weight of the base resin.

13. The shielded flat cable of claim 1, wherein the adhesive comprises a silane coupling agent in an amount of 0.01 to 5 parts by weight based on 100 parts by weight of the base resin.

14. The shielded flat cable of claim 1, wherein the adhesive comprises a hydrocarbon resin in an amount of 1 to 200 parts by weight based on 100 parts by weight of the base resin.

15. The shielded flat cable of claim 1, wherein the amount of the conductive particles is 1 to 70 parts by weight based on 100 parts by weight of the base resin.

Q1
cont'd. 16. The shielded flat cable of claim 1, wherein the average particle diameter of the conductive particles is 0.1 to 100 μm .


17. The shielded flat cable of claim 1, wherein a metal filler is used as the conductive particles.

Q2 19. The shielded flat cable of claim 1, wherein a flame retardant film is used as the substrate of the shielding member.

REMARKS

Entry and consideration of this Amendment is respectfully requested.

Respectfully submitted,


Robert J. Seas, Jr.
Registration No. 21,092

SUGHRUE MION, PLLC
2100 Pennsylvania Avenue, N.W.
Washington, D.C. 20037-3213
Telephone: (202) 293-7060
Facsimile: (202) 293-7860
RJS/amt
Date: March 12, 2002